




EUROLASTIC TC 30 G traffic black

fast-curing, 2-component polysulphide sealant, pourable, dispensing system-optimised, with an approved total deformation of 35 %, tested in accordance with TL Fug StB



-  Joint sealant: EUROLASTIC TC 30 G traffic
-  Primer: EUROLASTIC Primer U 12 G or EUROLASTIC Primer S2
-  Backing material: round PE cord (closed-cell)

Product description

EUROLASTIC TC 30 G traffic is a pourable, fast-curing, chemical-resistant, dispensing system-optimised, 2-component polysulphide-based (approx.35 %) joint sealant for sealing joints in traffic areas.

Area of application

- Sealing of dummy, press or expansion joints on traffic surfaces such as motorways, air traffic areas, etc.
- for indoor and outdoor use
- thanks to short curing times, areas being treated in renovation work can be quickly released for use.

Product characteristics

- fast-curing
- excellent resistance to notching and wear
- 2-component, isocyanate and solvent-free
- machinable
- elastic and durable over a wide temperature range (- 40°C to + 120°C)
- resistant to fuels, oils, de-icing agents, aircraft fuels and numerous other media.
- very high resistance to UV, weathering and ageing
- partially repairable (using cold vulcanising)
- outstanding recovery capability of > 90%



- not sticky, even at high temperatures
- approved total deformation of 35%

Colour	Black
---------------	-------

Substrate preparation	<p><u>New construction:</u></p> <p>The substrate temperature must be between +5°C and +35°C, and the temperature of the bonding surfaces must be at least 3°C above the prevailing dew point temperature. At the time of jointing, the bonding surfaces must be clean, free of oil and grease, dry and free of substances that could prevent adhesion.</p> <p><u>Renovation of joints in concrete surfaces:</u></p> <p>Use of our special EUROLASTIC U12G traffic primer makes re-cutting of joint flanks unnecessary in renovation work. See: "Substrate Preparation when Renovating Joints in Concrete surfaces" in the EUROLASTIC U12G traffic technical data sheet.</p>
------------------------------	---

Backfilling	To prevent three-flank adhesion and define the sealant thickness, a closed-cell polyethylene backer rod must be used to tightly and firmly fill the joint slots before applying the sealant. The rod must not be damaged during application.
--------------------	--

Primer	<p>Basically, EUROLASTIC TC 30 G traffic may only be applied to primed bonding surfaces.</p> <p>Absorbent substrates: EUROLASTIC Primer U12G traffic</p> <p>Non-absorbent substrates: EUROLASTIC Primer S2</p> <p>Bare steel and galvanised surfaces: EUROLASTIC Primer ZM (without approval) after curing EUROLASTIC Primer S2 must be applied.</p> <p>See primer matrix for further information</p>
---------------	--

Processing conditions	<p>Material temperature for manual processing: min. +10°C, max. +25°C</p> <p>Material temperature for mechanical processing: min. +10°C, max. +60°C</p> <p>Substrate temperature between: +5°C and +35°C Ambient temperature between: +5°C and +40°C</p>
------------------------------	--




The dew point must be taken into account! (+3°C above dew point)



Processing

EUROLASTIC TC 30 G traffic is supplied with the correct ratio of components A and B. Both components must be completely combined and thoroughly mixed for at least 3 - 5 minutes using a suitable, slow-running agitator at approx. 300 RPM. The mixing procedure must continue until a homogeneous, streak-free state is achieved. Place the mixture in a caulking gun or insert the container into a pressure tank with a hose and nozzle. Due to the rapid reaction time and associated short pot life, we recommend processing with a 2-component mixing and dosing system.

trafficable joint assembly



non-trafficable joint assembly



- a = chamfer face (3 to 10 mm)
- b = joint width (10 to 20 mm trafficable, non-trafficable up to 40 mm)
- d = joint sealant thickness
- dH = joint sealant adhesion or contact surface on the joint flank; $dH = d + 0.5 b$
- t = depth of joint slot

Joint Design Dimensions

Trafficable with pneumatic tyre vehicles			
	b	d	d _H
min.	10	10	15
max.	20	20	30

Non-trafficable			
	b	d	d _H
min.	10	10	15
max.	40	40	60



Cleaning

Fresh material can be removed from the tools with EUROLASTIC Cleaner G. Fully cured material requires mechanical cleaning.

Consumption	Joint width in mm	Joint depth in mm	Consumption in ml/m
	10	10	approx. 100
	15	12 - 15	approx. 180 - 225
	20	16 - 20	approx. 320 - 400
	25	20 - 25	approx. 500 - 625
	30	24 - 30	approx. 720 - 900
	35	28 - 35	approx. 980 - 1225
	40	32 - 40	approx. 1280 - 1600

Packaging

EUROLASTIC TC 30 traffic is supplied in 4l, 10l and 200l containers. A and B components are packaged separately.

Storage and shelf life

Store in a cool, dry place (+10°C to +25 °C). Under these conditions, the shelf life of unopened and undamaged original containers is 6 months.

Tests/ Approvals/Standards

EUROLASTIC TC 30 traffic complies with the European technical approval granted by DIBt (German Institute of Building Technology):

- Z-74.6-134
- TL-Fug StB / ZTV-Fug StB
- DIN EN 14188-2

Special instructions/protective measures

EUROLASTIC TC 30 G traffic may only be processed in well-ventilated areas. Suitable protective clothing must be worn when working. Waste and containers must be disposed of in a safe manner. Avoid release into the environment. Completely empty containers can be returned to the KBS/Interseroh circulatory system. The instructions in the corresponding safety data sheet must be strictly adhered to.



Technical data*		
Technical properties	Unit	Value
Material basis		Polysulphide/manganese dioxide
Mixing ratio A : B	Parts by	100 : 20
Number of components		2-component
Density at +23°C	g/cm ³	1.50 - 1.55
Solid volume at +23°C	%	100
Viscosity at +23°C		pourable
Processing time at +23°C/50% relative humidity	min	15 - 30
Curing time at +23°C/50% relative	h	2 - 4
Object and processing temperature	°C	from + 5 to + 35
Temperature resistance	°C	from + 40 to + 120

Mechanical properties	Unit	Value
Shore hardness		approx. 24
Approved total deformation	%	35
Tensile stress at +23°C	N/mm ²	approx. 0.30
Tensile stress at -20°C	N/mm ²	approx. 0.34
Recovery capability	%	> 90
Chemical resistance	see chemical resistance list	

* These are approximate values. The values are not intended for the preparation of specifications.

When processing the sealant with a heated 2-component mixing and dosing system (max. + 60 °C), divide the curing times by two.

The data was calculated at +23°C and 50% relative humidity. Higher temperatures and/or higher relative humidity may shorten or extend these times. All technical data, measurements and information in this data sheet are based on laboratory tests. Actual measured data may deviate in practice.

February 2017/We reserve the right to make technical changes and refinements. No liability assumed for advertising documents. Consultation of any kind, also due to any industrial property rights of third parties, shall be considered non-binding. The customer is solely responsible for the suitability of the goods for the particular intended use. All orders are subject to the seller's/manufacturer's terms and conditions for the sale and/or manufacture of the goods.
Reproduction not permitted.